

Walls and
Ceilings



09/2017

HYPERSID EXTRA



Product Description

Outstanding synthetic whitewash topcoat for interior walls (plaster walls, gypsum and concrete), with good coverage, breathes and doesn't turn yellow. Gives the home a feeling of cleanliness and space. The paint cannot wipe off. Economic solution for surfaces that do not require washability and scrub resistance. Bears Israeli standards mark 1637. Suitable for interior painting of ceilings, walls, concrete and plaster surfaces.

Surface Preparation

In order to obtain good results, the surface must be prepared thoroughly and carefully. Clean the surface well to remove any foreign body such as old whitewash, peeling paint, grease etc. Make sure the old paint is firmly attached to the infrastructure. On a new infrastructure apply an undercoat of Wonderspeed as a first coat to fill the spackle. If defects, holes etc. need to be repaired, fill with Maximo or with Gold Bond American Putty.

Application

Brush, roller or spraying (airless) - dilute with water according to the product instructions. First mixing must be done without the addition of water.

Clean-up

Soap and water.

Finish

Finish: Matt

Color: White. Can be tinted in pastel shades.

Technical Data

Theoretical Coverage*: 8 m² per L in 2 coats.

Dilution: with water, 20 % for first coat and 10 % for second coat.

Dry-Time

To touch: 1 hour.

To recoat: 2-3 hours.

Full cure: 24 hours.

Shelf Life

18 months in a cool, dry place.

Shelf Life

3, 5, 18 liters.

Health and Safety precautions: The material does not contain lead. During application it is advisable to wear goggles and ensure that the site is adequately ventilated. If the paint comes in contact with eyes, rinse well under running water and seek medical assistance. Keep the package tightly closed. Do not hang on the handle. Keep away from children. Do not mix materials not recommended by Nirlat.

*The practical coverage depends on a variety of factors such as type of surface, application method, paint shade, background color, the professionalism of the applicator as well as weather conditions. It is accepted to assume that it amounts 75 % of the theoretical coverage.

